



Kunjel Synergies Private Limited

15D, Everest House,
46C, J. L. Nehru Road
Kolkata – 700 071, India

Phone : 22881217 (3 Lines)

Fax : 22881223

Email : kunjel@vsnl.com

Web : www.kunjel.com

Specification of Recron 3S Polyester Triangular Fibre(6 mm & 12 mm Cut Length)

SR.No	Properties	Unit	Values
1	Cross Section		Triangular
2	Diameter	Microns	33 -36
3	Elongation	%	45 -55
4	Cut Length	Mm	6 & 12
5	Moisture(Flat)	%	<1.0
6	Melting Point	C	260
7	Softening Point	C	220
8	Specific Gravity	Cc/Gm	1.34 – 1.40

Recron 3S is non biodegradable and Chemical structure as shown below

